

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
5 February 2004 (05.02.2004)


PCT

(10) International Publication Number
WO 2004/011965 A1

- (51) International Patent Classification⁷: **G02B 1/10**
- (21) International Application Number:
PCT/KR2002/002251
- (22) International Filing Date:
29 November 2002 (29.11.2002)
- (25) Filing Language: Korean
- (26) Publication Language: English
- (30) Priority Data:
2002-0044786 30 July 2002 (30.07.2002) KR
2002-0044788 30 July 2002 (30.07.2002) KR
- (71) Applicant (for all designated States except US): **YUJIN-TECH21 CO., LTD.** [KR/KR]; B-325, Soonchunhyang Technology Business Incubator, San 646, Eupnae-ri, Sinchang-myeon, Asan-si, Chungcheongnam-do 336-885 (KR).
- (72) Inventor: **HA, Jin-Wook** [KR/KR]; 503-501 Wol-bongHyundai Apt., 1552, Ssangyong 2-dong, Cheonan-si, Chungcheongnam-do 330-092 (KR).
- (73) Inventors/Applicants (for US only): **HA, Jin-Heon** [KR/KR]; 701 DaelimYeoksam Apt., 761-10, Yeoksam-dong, Gangnam-gu, Seoul 135-080 (KR). **HONG, Jee-Nyu** [KR/KR]; 205-33 Maetan 4-dong, Paldal-gu, Suwon-si, Gyeonggi-do 442-374 (KR). **CHO, Seung-Hyun** [KR/KR]; 107-804 Ssangyong Apt., 873, Dang-dong, Gunpo-si, Gyeonggi-do 435-010 (KR).
- (74) Agents: **LEE, Sel-Jin et al.**; 17th Floor, City Air Tower, 159-9 Samsung-dong, Gangnam-gu, Seoul 135-973 (KR).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

[Continued on next page]

(54) Title: PLASTIC PHOTOCHROMIC LENS AND METHOD FOR PREPARATION THEREOF



(57) Abstract: Disclosed is a coating composition for a plastic photochromic lens and the plastic photochromic lens coated with the same. The coating composition includes a spiropyran photovisible color compound and/or spirooxazine photovisible color compound dissolved in toluene, and an acryl based binder. The plastic photochromic lens coated with the coating composition has advantages of short variable time, and good adhesion of the coating composition to the plastic lens and UV prevention effect without an undesirable haze phenomenon.

WO 2004/011965 A1



European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— *with international search report*

PLASTIC PHOTOCHROMIC LENS AND METHOD FOR PREPARTION THEREOF

Technical Field


5 The present invention relates, in general, to a plastic photochromic lens and a method of producing the same and, in particular, to a plastic photochromic lens having a short variable time, and a method of producing the same. Hereby, the variable time is defined as a time required for a lens to return to its original color when removed from the influence of sunlight or ultraviolet light after being discolored by exposure to the sunlight or ultraviolet light.

10 Background Art

As well known to those skilled in the art, a photochromic lens has a light color approaching to colorlessness indoors, but attains a dark depth of color outdoors when exposed to ultraviolet light or visible light having short wavelength. The photochromic lens is also called a 'Corning lens', originating from Corning Co. of
15 United States of America, which initially produced it. Because the photochromic lens includes fine crystals such as silver chloride (AgCl), silver bromide (AgBr), and silver iodide (AgI) dispersed in a glass or plastic lens, the depth of color is changed according to the irradiation amount of ultraviolet light. In other words, the photochromic lens is defined as a lens making a repetition of coloring when being
20 irradiated by ultraviolet light, and which becomes transparent when being not exposed to ultraviolet light.

As described above, the photochromic lens blocks ultraviolet light of sunlight to reduce eye strain and protect eyes from injurious ultraviolet light (UV-B) known for inducing cataracts, and since it filters 70 to 80 % of sunlight, it can be
25 applied to various applications. For example, the photochromic lens may act as sunglasses in summer when a great quantity of sunlight is irradiated, or outdoors.

Recently, various photovisible color compounds are used to produce photochromic lenses. The term photovisible color compound denotes a compound, being reversibly changed in terms of its color, discolored when being irradiated by ultraviolet light such as sunlight or mercury lamp light, and returns to its original color when not affected by ultraviolet light or stored in a dark room. Various types of photovisible color compounds have been synthesized, but these compounds do not have structural similarity. Initial studies of photovisible color compounds mostly focused on 1,3,3-trimethyl-indolinobenzospiropyran derivatives expressed by the following Formula:



(wherein, R1 and R2 are various substituents)

To improve the above derivative, various photovisible color compounds have been suggested. Among them, a representative compound is a spirooxazine compound disclosed in U.S. Pat. Nos. 4,215,010 and 4,342,668. In addition to the spirooxazine compound, pyran derivatives such as spiropyran or naphthopyran, fulgide, acridone, and naphthacene quinone are known in the art.

Meanwhile, conventionally, photovisible color compounds were directly incorporated in monomers to be used to produce a lens for spectacles. However, this case is applied to only lenses made of glass, and the variable time of the lens is too long to sufficiently satisfy consumers. Additionally, there was also attempts of applying the photovisible color compound to lenses made of plastic, but this case was disadvantageous in that it was cumbersome to perform a process of applying the photovisible color compound to plastic lenses because microwaves were used or the photovisible color compound were coated on the plastic lens under vacuum condition.


Disclosure of the Invention

Therefore, it is an object of the present invention to provide a novel plastic photochromic lens, which can be easily produced and has short variable time.


The present inventors developed a plastic photochromic lens with short variable time and good surface strength and ultraviolet ray filtering effect without an undesirable haze phenomenon by dissolving spiropyran based compounds, spirooxazin based compounds, or a mixture thereof in toluene in a predetermined mixing ratio, then incorporating an acryl based binder to produce the resulting solution, coating the resulting solution on a plastic lens, and heat-curing the coated lens.

According to an aspect of the present invention, a coating composition for a plastic photochromic lens comprising 1.5 to 5 wt% spiropyran compound defined by the following Formula I, or spirooxazine compound defined by the following Formula II, or a mixture thereof, 60 to 65 wt% toluene, and an acryl based binder to make 100 wt% of the coating composition is provided:

Formula I



Formula II



wherein,

R is alkyl with 1 to 30 carbon atoms,

R1 is alkyl, alkenyl, or alkoxy with 1 to 10 carbon atoms, or substituted or non-substituted phenyl,

R2 to R5 are independently hydrogen atom, halogen, cyano, nitro, or alkyl or
5 alkoxy with 1 to 6 carbon atoms, and

X is hydroxy, glycidoxy, amine, or dichlorotrioxazinoxy.

According to another aspect of the present invention, provided is a plastic
photochromic lens coated with a coating composition comprising 1.5 to 5 wt%
spiropyran compound defined by the Formula I, or spirooxazine compound defined
10 by the Formula II, or a mixture thereof, 60 to 65 wt% toluene, and an acryl based
binder to make 100 wt% of the coating composition.

According to still another aspect of the present invention, provided is a
method of producing a plastic photochromic lens comprising coating a surface of the
plastic photochromic lens with a coating composition including 1.5 to 5 wt%
15 spiropyran compound defined by the Formula I, or spirooxazine compound defined
by the Formula II, or a mixture thereof, 60 to 65 wt% toluene, and an acryl based
binder to make 100 wt% of the coating composition; and heat-curing the resulting
structure.

Brief Description of the Drawings

20 The above and other objects, features and other advantages of the present
invention will be more clearly understood from the following detailed description
taken in conjunction with the accompanying drawings, in which:

Fig. 1 is a graph showing an UV/Vis spectrum for a plastic photochromic
lens of the present invention, in which transmittance variation is plotted according to
25 wavelength of light irradiated into the plastic photochromic lens.

Best Mode for Carrying Out the Invention

According to the present invention, a spiropyran compound of Formula I, a spirooxazin compound of Formula II, or a mixture thereof is used as a photovisible color compound. The photovisible color compound is well known in the art, and for example, the spiropyran compound of Formula I is disclosed in US Pat. No. 5,241,075, and the spirooxazin compound of Formula II is used as a starting material in Korean Pat. No. 1994-0023831 and can be derived from the spirooxazin compound disclosed in US Pat. No. 4,342,668.

According to the present invention, the spiropyran compound of Formula I and the spirooxazin compound of Formula II may be used as the photovisible color compound alone or in a mixed form. It may be properly selected according to the desired color whether to use the above compounds alone or in a mixed form, depending on the type of the photovisible color compound. The spiropyran based compound and spirooxazin based compound absorb ultraviolet light from the sunlight and emit as violet, yellow, green, brown, red, or blue in color, but becomes transparent when it is not exposed to UV.

Photovisible color compounds of the present invention can be mixed together while being dissolved in toluene to produce a solution having a different color from the original colors of the components. For example, if a yellow liquid is mixed with a blue liquid to produce a coating liquid composition, a surface of the plastic lens coated with the coating liquid composition will be green. Meanwhile, an acryl based binder is useful as a binder of the present invention, and the binder may be selected from the group consisting of an organic binder, an inorganic binder, or a mixture thereof. In the present invention, the binder can be obtained as a commercial binder, or produced according to a conventional binder producing method.

Generally known as a solvent for dissolving the photovisible color compound is an organic solvent such as hexane, xylene, toluene, methylene chloride,

ethyl acetate, and butyl acetate. According to the present invention, the spiropyran compound of Formula I, or the spirooxazin compound of Formula II, or a mixture thereof is most soluble in toluene and methylene chloride. However, in the case of using methylene chloride as the solvent, an undesirable haze phenomenon occurs on the plastic lens coated with the coating composition. Accordingly, toluene is most preferably used as the solvent in the present invention.

When the photovisible color compound of Formula I or II is dissolved in toluene, color of the resulting solution was varied according to the solubility. The results are described in Table 1.

TABLE 1

| Color | Solubility (%) |
|--------|----------------|
| Violet | 3.0 |
| Blue | 5.0 |
| Yellow | 5.0 |
| Red | 5.0 |

According to the present invention, the coating composition for the plastic photochromic lens comprises 1.5 to 5 wt% spiropyran compound defined by Formula I, or spirooxazine compound defined by Formula II, or a mixture thereof, 60 to 65 wt% toluene, and an acryl based binder to make 100 wt% of the coating composition. For example, when an acryl based binder content is undesirably low, a coated layer is not completely attached to a surface of the plastic lens, thereby reducing adhesion and hardness. On the other hand, when the binder content is excessively high, viscosity is increased and the coated layer becomes thick, thereby making the surface of the coated layer uneven. Additionally, when the toluene content is undesirably high, depth of the color of the coated layer is lowered unless the photovisible color compound is additionally added. In other words, when toluene is added to the photovisible color compound in such an amount that the concentration of the photovisible color compound in toluene is less than the maximum soluble amount,

depth of the color of the coated layer is lowered. On the other hand, when toluene is mixed with the photovisible color compound in such an amount that the concentration of the photovisible color compound in toluene is more than the maximum soluble amount, the photovisible color compound is not completely dissolved in toluene and will be precipitated on the bottom.


According to the present invention, the composition including the photovisible color compound of Formula I and/or Formula II, toluene, and the acryl based binder may be coated on the plastic lens by various coating processes such as a manually coating process, a spin coating process, a dip coating process, or a spray coating process.

As described above, the plastic lens is coated with the coating composition of the present invention, and heat-cured to produce a plastic photochromic lens. However, the photovisible color compound of the present invention has poor heat resistance. Therefore, if the curing temperature is too high, the plastic lens is not able to fulfill its function of changing color. On the other hand, when the curing temperature is too low, it takes a long time to cure the coating composition and occasionally curing is not completely conducted, thus reducing strength of the coated layer. Accordingly, it is preferable that the curing temperature is 30 to 80 °C.

A better understanding of the present invention may be obtained in light of the following examples which are set forth to illustrate, but are not to be construed to limit the present invention.

EXAMPLE 1



3 wt % photovisible color compound (manufactured by Unitech Co., Korea) defined by the following Formula was dissolved in 64 wt% toluene.



33 wt % acryl based organic · inorganic complex binder (A9540 manufactured by Aekyung Chemical Co., Korea) was added to this solution to produce a coating composition.

EXAMPLE 2

5 5 wt % mixture of photovisible color compound (manufactured by Unitech Co., Korea) defined by the following Formulae was dissolved in 65 wt% toluene.



10 30 wt % acryl based organic · inorganic complex binder (A9540 manufactured by Aekyung Chemical Co., Korea) was added to this solution to produce a coating composition for a plastic photochromic lens.

EXAMPLE 3

The coating composition obtained from Example 1 was spin-coated on a surface of a plastic lens, and heat-cured at 80°C to produce the plastic photochromic lens.

5

EXAMPLE 4

The coating composition obtained from Example 2 was dip-coated on a surface of a RGP plastic lens, and heat-cured at 80°C to produce the plastic photochromic lens.

EXPERIMENTAL TEST 1

10

Test of Variable time

The plastic photochromic lens obtained from Example 3 was exposed to sunlight. Then, the exposed plastic photochromic lens turned brown. The brown plastic photochromic lens lost its color and became transparent within 1 min after the lens was moved to indoors where exposure to sunlight was blocked.

15

EXPERIMENTAL TEST 2

Measurement of Ultraviolet light blocking ratio

The plastic photochromic lens obtained from example 3 was measured in terms of transmissivity of ultraviolet light using a UV/Vis spectrum. The results are described in FIG. 1.

20

From the results of FIG. 1, it can be seen that the plastic photochromic lens of the present invention has a 99 % or higher ultraviolet ray blocking ratio.

EXPERIMENTAL TEST 3

Measurement of Adhesive strength

The plastic photochromic lens obtained from example 3 was measured in terms of adhesive strength according to the KS D 6711-92 test procedure. The results were 100/100. This proves that the plastic photochromic lens according to the present invention has excellent adhesive strength.

Industrial Applicability


As described above, a plastic photochromic lens according to the present invention is advantageous in that its variable time is short, an undesirable haze phenomenon does not occur, and it has good adhesion of a coating composition to a plastic lens and ultraviolet ray filtering effect.

The present invention has been described in an illustrative manner, and it is to be understood that the terminology used is intended to be in the nature of description rather than of limitation. Many modifications and variations of the present invention are possible in light of the above teachings. Therefore, it is to be understood that within the scope of the appended claims, the invention may be used otherwise than as specifically described.


What is claimed is:

1. A coating composition for a plastic photochromic lens, comprising 1.5 to 5 wt% spiropyran compound defined by the following Formula I and/or spirooxazine compound defined by the following Formula II; 60 to 65 wt% toluene;
 5 and an acryl based binder to make 100 wt% of the coating composition.

Formula I



Formula II



10

(wherein,

R is alkyl with 1 to 30 carbon atoms;

R1 is alkyl, alkenyl, or alkoxy with 1 to 10 carbon atoms, or substituted or non-substituted phenyl;

15

R2 to R5 are independently hydrogen atom, halogen, cyano, nitro, or alkyl or alkoxy with 1 to 6 carbon atoms; and

X is hydroxy, glycidoxy, amine, or dichlorotrioxazinoxy)


2. A plastic photochromic lens coated with the coating composition according to claim 1.

3. A method of producing a plastic photochromic lens, comprising:
coating a surface of a plastic lens with the coating composition according to
5 claim 1; and
heat-curing the resulting structure.

4. The method according to claim 3, wherein the heat-curing is performed at the temperature of 30 to 80°C.

1/1

FIG. 1



INTERNATIONAL SEARCH REPORT

International application No.
PCT/KR02/02251

A. CLASSIFICATION OF SUBJECT MATTER

IPC7 G02B 1/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 G02B 1/00, 1/10, 5/00, 5/23

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Korean Patent and Applications for Inventions since 1947

Korean Utility Models and Applications for Utility Models since 1947

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKipass

C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|-------------|--|-----------------------|
| X Y | US 5,166,345 A (Toray Industries, Inc.) 24 Nov. 1992 see column 9 lines 4-14 | 1,2 3,4 |
| Y Y Y | US 4,756,973 A (Kureha Kagaku Kogyo Kabushiki Kaisha) 12 Jul. 1988 see column 2 lines 23-45 see column 3 line 55 - column 4 line 58 see column 9 lines 11-25, see column 11 lines 12-19 | 1 1-3 4 |
| Y | US 5,581,090 A (Solartech Enterprises, LLC) 3 Dec. 1996 see claim 1, column 5 line 57 - column 6 line 48 | 1,2 |
| A | US 4,994,208 A (PPG Industries, Inc.) 19 Feb. 1991 see the whole document | 1-4 |
| A | US 4,929,693 A (Toray Industries, Inc.) 29 May 1990 see the whole document | 1-4 |
| A | US 5,833,885 A (Pilkington PLC.) 10 Nov. 1998 see the whole document | 1-4 |

☒ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family


Date of the actual completion of the international search

28 APRIL 2003 (28.04.2003)

Date of mailing of the international search report

29 APRIL 2003 (29.04.2003)

Name and mailing address of the ISA/KR

 Korean Intellectual Property Office
920 Dunsan-dong, Seo-gu, Daejeon 302-701,
Republic of Korea

Facsimile No. 82-42-472-7140

Authorized officer

KIM, Sang Hee

Telephone No. 82-42-481-5974



INTERNATIONAL SEARCH REPORT

International application No.

P 02/02251

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

| Category* | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|-----------|--|-----------------------|
| A | US 6,194,511 B1 (Tokuyama Corporation) 27 Feb. 2001 see the whole document | 1-4 |